

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 October 2004 (21.10.2004)

PCT

(10) International Publication Number
WO 2004/090052 A1

(51) International Patent Classification⁷: **C09D 5/16**,
A01N 37/18, 37/20, 37/36, 43/24, 47/06, 47/08

(21) International Application Number:
PCT/EP2004/003710

(22) International Filing Date: 7 April 2004 (07.04.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03008352.1 10 April 2003 (10.04.2003) EP

(71) Applicant (for all designated States except US): **SYM-RISE GMBH & CO. KG** [DE/DE]; Mühlenfeldstrasse 1, 37603 Holzminden (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **PELZER, Ralf** [DE/DE]; Im Schlossgarten 3, 37699 Fürstenberg (DE). **WÖHRLE, Ingo** [DE/DE]; Fahrenbreite 23a, 37603 Holzminden (DE).

(74) Agent: **STILKENBÖHMER, Uwe**; Eisenführ, Speiser & Partner, Postfach 10 60 78, 28060 Bremen (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

"EXPRESS MAIL" LABEL NO.: **EV550579921US**
I HEREBY CERTIFY THAT THIS PAPER IS BEING DEPOSITED WITH THE UNITED STATES POSTAL SERVICE "EXPRESS MAIL POST OFFICE TO ADDRESSEE" SERVICE UNDER 37 CFR. 1.10 IN AN ENVELOPE ADDRESSED TO: THE COMMISSIONER OF PATENTS, P.O. BOX 1-50, ALEXANDRIA, VA 22313-1450, ON THIS DATE. THE COMMISSIONER IS HEREBY AUTHORIZED TO CHARGE ANY FEES ARISING HEREFROM AT ANY TIME TO DEPOSIT ACCOUNT 16-0877.

DATE

SIGNATURE

(54) Title: NON-TOXIC COATING COMPOSITION, METHODS OF USE THEREOF AND ARTICLES PROTECTED FROM ATTACHMENT OF BIOFOULING ORGANISMS

(57) Abstract: The present invention relates to coating compositions comprising menthol and/or isopulegol and at least one further active ingredient which provide protection to surfaces coated therewith from attachment of various biofouling organisms. These compositions are advantageously used in paint, varnish and sealant formulations.

WO 2004/090052 A1

10/553090**JCO9 Rec'd PCT/PTO 11 OCT 2005**

Non-toxic coating composition, methods of use thereof and articles protected from attachment of biofouling organisms

The present invention relates to non-toxic coating compositions comprising active ingredients which provide protection to surfaces coated therewith from attachment of various biofouling organisms. These compositions are advantageously used in paint, varnish and sealant formulations.

- 5 The present invention in particular relates to non-toxic coating compositions comprising a mixture of (i) menthol and/or isopulegol and (ii) at least one further active ingredient (as further defined below).

Biocides are commonly used in a variety of coating materials having diverse applications. In marine paints, for example, biocides protect underwater
10 structures against attachment of a wide range of biofouling organisms, such as algae, barnacles, ship worms and other aquatic nuisance species. In lakes and rivers, biocides are used to protect underwater structures from freshwater organisms, such as zebra mussels. It has been found that microorganisms, their

viscous, bio-organic product and absorbed organic matter constitute a tenacious slime which forms on the surfaces of submerged structures. The initial organisms in this fouling sequence are bacteria, followed by a biotic progression of diatoms, hydroids, algae, bryozoans, protozoans and finally macrofoulants. Macrofoulants
5 tend to be rugophilic, i.e., settling on roughened surfaces in preference to smooth surfaces.

The fouling of ship bottoms is a longstanding problem, which contributes to speed reduction and increased fuel consumption. The problem of fouling is not limited to ships, however, but extends to other underwater structures, as well.
10 Buoys can shift due to the excessive weight of fouling organisms. Wood pilings in berthing facilities undergo structural weakening and ultimate destruction due to ship worm and fungal attack. The fouling of intake screens of municipal water supply systems can lead to reduced flow rates and accelerated corrosion. Concrete or ferro-cement structures, e.g., dams, are also adversely affected by
15 biofouling organisms.

It is understood by those of skill in the art that a marine coating must be water resistant in order to provide practical and effective protection. The expression „water resistant,“ as used in describing the composition of the invention, refers to its ability to provide a durable, protective barrier that can effectively withstand
20 hydrolytic attack and is essentially impermeable to water. Water resistance is intrinsically important to marine coatings because, for example, it is prohibitively expensive to re-coat most items in marine service, as they must be put into dry-dock or otherwise removed from the water in order to be re-coated. It is also desirable, for example, to minimize the time and expense of cleaning fouling
25 organisms from the coated surface. The protection provided by a marine coating, therefore, whether it be against corrosion, fouling, abrasion, etc., should be effective over a period of at least months, and, ideally, over at least several years. A coating composition that is not water resistant would be short lived in the water rather than meeting the performance criteria of a marine coating.

30

The majority of commercial anti-fouling coatings include organometallic compounds which are potent biocides that leach over time from the coating material. Tributyltin (TBT), for example, is known to be highly toxic to shellfish.

Anderson and Dally, Oceans '86, IEEE Publication #86 CH2363-0 (1986). Acute toxicity in invertebrates and vertebrates occurs at concentrations as low as 1 μ g (micrograms) per liter. Laughlin et al., Mar. Ecol. Prog. Ser., 48: 29-36 (1988). Cuprous oxide and zinc oxide, which are other commercially used antifoulants, also function by releasing heavy metals, i.e., copper and zinc, into the marine environment.

In latex architectural paints and wood stains, biocides provide in-can protection against microbiological contamination that can cause odor and changes in viscosity and color, and protect the dried film and underlying substrate from damaging microorganisms. Such coating materials must likewise be water resistant in order to provide effective protection to coated surfaces.

Biocides are also conventionally utilized in elastomeric coatings, adhesives, caulks, glazing compounds, joint cements and the like, which are also water resistant.

Because certain biocides currently used in the above-mentioned products have been shown to be ecologically harmful, a number of international agencies, whose missions include monitoring environmental quality, are urging the curtailment and eventual termination of their manufacture and use. A proposal has been made by the International Maritime Organization (IMO), for example, that all antifoulant coatings that contain TBT, as well as other organotin compounds which have a toxic effect on a wide range of marine organisms, would be banned worldwide by the year 2003. Consequently, manufacturers of such products are faced with the prospect of changing existing formulations to include alternative agents that are, at once, effective in preventing attachment and growth of biofouling organisms and environmentally benign. Other criteria that must be taken into account in developing acceptable substitutes for ecologically harmful biocides include chemical compatibility with other components in the coating composition, physical compatibility with the dried film and substrate to which the coating is applied, the safety of those handling or using the substitute agents themselves or coating materials containing them and the cost of their production.

WO 01/95718 relates to non-toxic coating compositions which provide protection to surfaces coated therewith from attachment of various biofouling organisms using mainly terpenes and terpene derivatives, in particular (-)-menthol, (-)-trans-p-menthan-3,8-diol, (-)-menthyl chloride, 3-[[5-methyl-2-(1-methylethyl)cyclohexyl]oxy]-1,2-propanediol, (-)-isopulegol and (-)-menthone. A mixture consisting of equal parts of (-)-menthol and (-)-trans-p-menthan-3,8-diol is described in Example 7 (page 15 and 16), which resulted in a lower percentage of settlement of barnacles.

It is therefore one object of the present invention to provide paints or coating compositions with comparable or better antifouling activity, preferably over a prolonged period of time, especially 3 - 5 years.

Summary of The Invention

In accordance with a first aspect, the present invention provides a (preferably non-toxic) paint or coating composition comprising


(i) menthol and / or isopulegol

5 and

(ii) a compound selected from the group consisting of

a) menthyl esters of a (preferably natural occurring) hydroxycarboxylic acid having 2 to 6 carbon atoms, which are in turn optionally esterified by C₁-C₄ carboxylic acids on the hydroxy group;

10 b) compounds of formula (I):



(I)

wherein


15 R¹ represents a C₂-C₆-alkylene radical having at least 1, but not more than 3, hydroxy group(s) and

either R² and R³ independently of one another represent C₁-C₁₀-alkyl which is optionally substituted by 1 to 3 radicals from the group comprising hydroxy, amino and halogen, or C₅-C₇-cycloalkyl, or C₆-C₁₂-aryl, with the proviso that the
20 total amount of the carbon atoms of R² and R³ is not less than 3,

or

R^2 and R^3 together represent an alkylene radical which, together with the carbon atom which carries the radicals R^2 and R^3 , forms a 5-7-membered ring, it being possible for this alkylene radical, for its part, to be substituted by C_1 - C_6 -alkyl groups;

5 c) compounds of formula (II):



(II)

10 wherein

R^a denotes C_4 - C_{20} -alkyl, C_5 - C_{20} -cycloalkyl or -heterocycloalkyl or C_5 - C_{20} -alkoxy, C_6 - C_{12} -aryl, C_5 - C_{10} -heteroaryl or C_7 - C_{11} -aralkyl,

R^b denotes an $m + w + n$ -valent aliphatic C_1 - C_8 radical, a cycloaliphatic or heterocycloaliphatic C_3 - C_{15} radical, an araliphatic C_7 - C_{20} radical, an alkoxy- or
15 acyloxy-containing aliphatic C_3 - C_{15} radical,

A and B independently of one another denote -O-, -S- or -NH-,

Y denotes hydroxy, C_1 - C_{10} -alkoxy, C_2 - C_6 -acyloxy, amino, mercapto or -O-Z-O-


Z denotes C_1 - C_6 -alkylene,

w denotes the valency of the radical Y and

20 m and n independently of one another denote integers from 1 to 8, with the proviso that the sum of $m + n$ is not more than 12

(note: these compounds of group c) are particularly preferred)

d) compounds of formula (III):




(III)

5 wherein

R = H and k is an integer from 1 to 4, or R = CH₃ and k is an integer from 0 to 4;

e) compounds of formula (IV):




(IV)

10 wherein

R' is H or an alkyl, cycloalkyl, alkenyl, cycloalkenyl, hydroxyalkyl, alkynyl, acyloxyalkyl, alkoxyalkyl, aminoalkyl, acylaminoalkyl, carboxyalkyl radical or an alkylcarboxyalkyl radical of the formula -C_pH_{2p}COOR'', wherein -C_pH_{2p} is a
 15 straight or branched chain alkylene group in which p is an integer from 1 to 6 and R'' is C₁-C₈-alkyl, each of said radicals containing up to 25 carbon atoms, and

R'' is hydroxy or an alkyl, cycloalkyl, alkenyl, cycloalkenyl, hydroxyalkyl, alkynyl, acyloxyalkyl, alkoxyalkyl, aminoalkyl, acylaminoalkyl, carboxyalkyl radical or an alkylcarboxyalkyl radical of the formula $-C_pH_{2p}COOR'''$, wherein $-C_pH_{2p}$ is a straight or branched chain alkylene group in which p is an integer from 1 to 6 and R''' is C_1 - C_8 -alkyl, each of said radicals containing up to 25 carbon atoms; with the proviso that when R' is hydrogen R''' may also be an aryl radical of up to 10 carbon atoms selected from benzyl and substituted phenyl wherein the substituents are selected from C_1 - C_4 alkyl, hydroxy and C_1 - C_4 -alkoxy, nitro and halogen;

f) compounds of formula (V):



(V)

wherein

$R^\#$ is C_1 - C_5 -alkyl, C_1 - C_8 -hydroxyalkyl or alkylcarboxyalkyl with up to 6 carbon atoms,

R^X is hydrogen or C_1 - C_5 -alkyl; and

R^Y and R^Z independently are C_1 - C_5 -alkyl,

with the provisos that

R^X , R^Y and R^Z together provide a total of at least 5 carbon atoms, preferably 5-10 carbon atoms, and

when R^X is hydrogen, R^Y is C_2 - C_5 -alkyl and R^Z is C_3 - C_5 -alkyl and at least one of R^Y and R^Z is branched, preferably in alpha or beta position relative to the carbon atom marked (*) in the formula (V);

and

- 5 (iii) a film forming agent.

Herein, the use of the compounds of formula (II) is particularly preferred. The corresponding aspect(s) of the invention are particularly valuable. Correspondingly, any reference to "compounds listed under ii) a) to f)" is also to be understood as a reference to the compounds of group ii) c) alone.

- 10 Examples of alkyl groups include methyl, ethyl, n-propyl, isopropyl, n-butyl, sec.-butyl, isobutyl and tert.-butyl.

Examples of alkenyl groups include ethenyl, propenyl, 2-methyl propenyl, n-butenyl.

- 15 Examples of alkoxy groups include methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, isobutoxy, sec.-butoxy, tert.-butoxy.

All of the isomeric forms of menthol and/or isopulegol and the compounds listed under ii) a) to f), above, may be used in practicing this invention, including structural isomers and stereoisomers.

- 20 The mixture of menthol and/or isopulegol and the compounds listed under ii) a) to f), above, is present in the coating composition in an amount effective to inhibit the attachment of biofouling organisms on a surface to which the composition is applied as a coating.

Preferably, the compounds listed under ii) a) to f) above are present in an amount of from 0.01 to about 50 percent by weight of the composition.

- 25 Also in accordance with this invention, there is provided a paint comprising the above-described paint or coating composition, preferably a marine paint.

There are also provided in accordance with this invention certain methods of use of coating materials including menthol and/or isopulegol and the compounds listed under ii) a) to f) above, in particular the compounds of formula II as listed under ii) c) above. One such method involves protecting a surface exposed to an aqueous environment from fouling organisms present in the aqueous environment by applying (e. g., by brushing, spraying or dipping) to such surface a coating including menthol and/or isopulegol and at least one, i. e. one or more of the compounds listed under ii) a) to f). Another method entails protecting a coated surface from attachment and growth of undesired fungal organisms, such as molds, mildew and the like by including in the coating formulation applied to such surface at least one of the above-described compounds.

As another aspect of this invention, articles are provided which have a coating of the composition described herein on at least a portion of the surface thereof, which provides protection against exposure to the deleterious effects of biofouling organisms.

The coating composition described above satisfies all of the above-noted criteria for an environmentally acceptable coating product, in that it provides effective protection against attachment and growth of biofouling organisms, while producing no known ecologically harmful effect. Moreover, menthol, isopulegol and the compounds listed under ii) a) to f), in particular those of group ii) c), above have been shown to be compatible, both chemically and physically, with conventional marine and other paint formulations, are safe to handle and can be obtained at a relatively low cost.

Detailed Description of The Invention


It has been discovered in accordance with the present invention, that the compounds listed under ii) a) to f), above, and particularly those of group ii) c) are useful for inhibiting the attachment of biofouling organisms on surfaces, particularly those of underwater structures, to which a coating composition comprising one or more such compounds is applied, in particular when they are combined with menthol and/or isopulegol. Such a mixture or combination shows a synergistically enhanced activity in comparison with menthol and/or isopulegol.

As used herein, the term "biofouling organisms" refers to any and all organisms that participate in the fouling sequence in both saltwater and freshwater environments, including, without limitation; bacteria, diatoms, hydroids, algae, bryozoans, protozoans and macro-foulants.

The menthol according to the present invention advantageously is l-menthol or racemic menthol, preferably l-menthol.

The isopulegol according to the present invention advantageously is (-)-isopulegol or racemic isopulegol, preferably racemic isopulegol.


Advantageous compounds which have been found to be effective antifouling agents for a prolonged period of time are compounds selected from (ii) a), above, i.e. menthyl esters, in particular esters of l-menthol, of beta-hydroxybutyric acid, alpha-hydroxyisovaleric acid, alpha-hydroxycaproic acid, alpha-hydroxy-alpha-methyl-valeric acid, glycolic acid and lactic acid, preferred is menthyl lactate. This compound is commercially available, e.g. as Frescolat ML[®] (Haarmann & Reimer). Particularly preferred is the ester of l-menthol and racemic lactic acid (l-menthyl lactate).




l-menthyl lactate

Menthyl esters according to (ii) a), above, are well known and described in DE 26 08 226, incorporated herein by reference in its entirety.


Advantageous compounds which have been found to be effective antifouling agents for a prolonged period of time and are selected from (ii) b), above, are compounds of formula (Ia) to (Id),




(Ia)



(Ib)




(Ic)




(Id)

wherein R¹ has the meaning described above, preferably R¹ denotes



The preferred compound of (ii) b) is menthone glycerin acetal. This compound is commercially available, e.g. as Frescolat MGA® (Haarmann & Reimer). Depending on the starting material and the preparation methods used, menthone glycerin acetal can be used as mixtures of optical isomers or in the form of the


pure isomers. Particularly preferred is a mixture of diastereomers of formula (Iaa).




(Iaa)

The compounds according to (ii) b), above, in particular the formulas (Ia) to (Id), above, are well known and described in EP 0 507 190, incorporated herein by reference in its entirety.


Particularly advantageous compounds which have been found to be effective antifouling agents for a prolonged period of time are compounds selected from (ii) c), above. Compounds of formulas (IIa) to (IIj) are particularly preferred.




(IIa)




(IIb)






(IIc)




(IIId)


5




(IIe)



(IIIf)




(IIg)




(IIh)

10




(IIIi)




(IIIj)

- Particularly preferred are menthol glycol carbonate (IIa), menthol propyleneglycol carbonate (IIb) and menthol glycerin carbonate (IIc). Depending on the starting material and the preparation methods used, the carbonates (IIa), (IIb) and (IIc) can be used as mixtures of optical isomers or in the form of the pure isomers. Preferred are the compounds (IIa), (IIb) and (IIc) as derived from l-menthol. The compounds according to (ii) c), above, in particular the compounds of formulas (IIa) to (IIj), above, are well known and described in EP 0 583 651, incorporated herein by reference in its entirety.
- Advantageous compounds which have been found to be effective antifouling agents for a prolonged period of time are compounds and are selected from (ii) d), above, are menthyl methoxyacetate and menthyl 3,6-dioxaheptanoate, particularly preferred are the menthyl esters of l-menthol. The compounds according to (ii) d), above, are well known and described in DE 191 547 and EP 1 034 161, incorporated herein by reference in their entirety.

A preferred compound which has been found to be an effective antifouling agent for a prolonged period of time and is selected from (ii) e), above, is N-ethyl-p-menthane-3-carboxamide of formula (IVa) (also known as WS-3, commercially available) which can be used as a mixture of optical isomers or in the form of the pure isomers, advantageous is the isomer of formula (IVb).




(IVa)



(IVb)

- The compounds according to (ii) e), above, are well known and described in US 4,136,163, incorporated herein by reference in its entirety.

A preferred compound which has been found to be an effective antifouling agent for a prolonged period of time and is selected from (ii) f), above, is 2-isopropyl-N-2,3-trimethylbutanamide of formula (Va) (also known as WS-23, commercially available).



(Va)

The compounds according to (ii) f), above, are well known and described in US 4,230,688, incorporated herein by reference in its entirety.

The ratio by weight of menthol and/or isopulegol to the total of compounds listed under ii) a) to f), above, is typically between 20 : 1 and 1 : 5, preferably between 10 : 1 and 1 : 2. When menthol and isopulegol are used together in the composition, the ratio of menthol : isopulegol typically lies in the range of 1 : 10 and 10 : 1, preferably between 1 : 5 and 5 : 1.

In a preferred embodiment a combination of menthol, isopulegol and menthol propyleneglycol carbonate, is used; the ratio of isopulegol : menthol being 3 : 1 to 1 : 2, the ratio of menthol propyleneglycol carbonate : isopulegol being 2 : 1 - 1 : 5. In a particular preferred embodiment the ratio menthol propyleneglycol carbonate : isopulegol : menthol is about 1 : 2 : 1.

The compounds used in the present invention may be synthesized from readily available starting materials using known synthetic routes or are commercially available.

Optionally, the compositions according to the invention may comprise cyclic alpha-keto enamines, as described in J. Agric. Food Chem. 49, 5383-5390 (2001), preferably 5-methyl-4-(1-pyrrolidinyl)-3-[2H]-furanone, 4,5-dimethyl-3-(1-pyrrolidinyl)-2[5H]-furanone and 4-methyl-3-(1-pyrrolidinyl)-2[5H]-furanone.

Menthol and/or isopulegol and the compounds listed under ii) a) to f), above, may be included in a conventional paint composition as the sole antifouling agent, or added in combination with other antifouling agents, biocides, antibiotics, and natural products or extracts to produce an additive or synergistic effect on attachment of biofouling organisms. Examples of (non-toxic) antifouling agents include decalactone, alpha-angelicalactone, alpha-santonin, alpha-methyl-gamma-butyrolactone and alantolactone. Exemplary biocides (fungicides and algaecides) include isothiazolones (such as Sea Nine-211), zinc omadine® (2-pyridinethiol-1-oxide, zinc complex), chlorothalonil, and triazine algaecide. A typical example of a suitable antibiotic is tetracycline, which is a registered antifoulant.

Menthol and/or isopulegol and the compounds listed under ii) a) to f), above may also be combined with organometallic antifoulants, such as tributyl tin or triphenyl tin, or inorganic antifoulants such as zinc oxide or cuprous oxide, to reduce the total amount of (such) toxic antifoulants in a given coating material.

The film-forming component of the composition of the present invention may be any component or combination of components that is readily applied and adheres to the surface to be protected when the surface is submerged. The specific film-forming component to be selected for a particular application will vary depending on the material and construction of the article to be protected and the performance requirements thereof. After a surface is provided with a protective coating in accordance with this invention, the active ingredients menthol and/or isopulegol and at least one compound listed under ii) a) to f), e. g. a compound of group ii) c), that are present in the coating comes in contact with biofouling organisms, thereby preventing their attachment. A variety of synthetic polymers are useful for this purpose. Examples of suitable polymer resins include unsaturated polymer resins, vinyl ester, vinyl acetate, and vinyl chloride based resins and urethane based resins. Unsaturated polyester resins are formed from unsaturated acids and anhydrides, saturated acids and anhydrides, glycols, and glycol monomers. Preferred film-forming components are mixtures of natural rosin and vinyl chloride-vinyl acetate co-polymers. A commercial marine paint vehicle which is suitable for the practice of this invention is Amerlock 698, a

product of Ameron International, Pasadena, CA. Comparable marine paint vehicles are also available from Jotan, AS, Sandefjord, Norway.

The coating composition of the invention may include components in addition to menthol and/or isopulegol and the compounds listed under ii) a) to f), above, and
5 a film-forming component, so as to confer one or more desirable properties, such as increased or decreased hardness, strength, increased or decreased rigidity, reduced drag, increased or decreased permeability, or improved water resistance. The selection of a particular component or group of components to impart such properties are within the capabilities of those having ordinary skill in
10 the art.

The coating composition of the present invention may be used in various paint formulations, marine paints being preferred.

The percentage of the active agent (be it a single compound or a mixture), i.e. one or more of the compounds listed under ii) a) to f), and in particular one or
15 more of the compounds of group ii) c), above and, preferably, menthol and/or isopulegol, in the coating composition required for effective protection against biofouling agents may vary depending on the active agent itself, the chemical nature of the film former, as well as other additives present in the composition that may influence the effectiveness of the active agent. Generally, the active
20 agent comprises between about 0.01 and about 50 percent of the coating composition by weight, and preferably between about 0.1 and about 10 percent by weight of the composition.

The compounds listed under ii) a) to f), above and, if present, menthol and/or isopulegol may be included in a non-toxic paint, coating composition or paint
25 formulation during the paint/coating manufacturing processes or added to the paint/coating base mixture at the time of use. Menthol and/or isopulegol (if present) and the compounds listed under ii) a) to f), above, can be simply mixed into the film-forming components. This is known as a „free association“ coating, which allows leaching of the menthol and/or isopulegol and the compounds listed
30 under ii) a) to f), above, from the film-forming components. The antifouling agent may be covalently bound to the resin, known as „ablative or self-polishing coating“ and is released only after the bond hydrolyzes in seawater. Controlled

hydrolysis permits a slow release rate while creating a hydrophilic site on the resin. A new layer of bound menthol and/or isopulegol and compounds listed under ii) a) to f), above, is then exposed when the hydrolyzed layer is washed away. See also, Tiller et al. in Proc. Natl. Acad. Sci., 2001, 98, 5981-5985, the
5 entire contents of which are incorporated by reference herein. Furthermore, menthol and/or isopulegol (if present) and the compounds listed under ii) a) to f), above, may also be incorporated with slow release materials which permit the controlled release of the compounds into the matrix of the coating, thereby prolonging the effectiveness of the coating and reducing the amount of
10 compounds necessary to produce the antifouling effect. Encapsulation into such slow release materials also protects menthol and/or isopulegol and the compounds listed under ii) a) to f), above, from the harsh chemical milieu of the coating and would reduce degradation of the compounds while trapped in the resin, if they were susceptible to degradation. Examples of these slow release
15 materials include: a) microcylinders composed of metallic cylinders or modified molecules such as 1,2-bis-(10,12-tricosadinoyl)-glycer-3-phosphocholine; (b) liposomes; and (c) cyclodextrins.

While not wishing to be bound to a specific theory regarding the mechanism of
20 action, it is believed that the active agent of the coating composition of this invention, i.e. menthol and/or isopulegol and at least one of the compounds listed under ii) a) to f), above, function by producing an environment at the surface of a coated substrate which repels biofouling organisms, thereby preventing their attachment and growth on the coated surface. In this connection, it is
25 conjectured that the menthol and/or isopulegol and the compounds listed under ii) a) to f), above, act as antifoulants by interacting with the cold receptors of the fouling organisms to induce chemotaxis. It is believed that this interaction need not be permanent, and accordingly there is no need for the menthol and/or isopulegol and the compounds listed under ii) a) to f), above, to be irreversibly
30 consumed in order to exhibit antifoulant activity. It would therefore be desirable to attach the menthol and/or isopulegol and the compounds listed under ii) a) to f), above, covalently to the film-forming agent, thereby obtaining a coating whose antifoulant ingredient will not be released into the marine environment. The

inhibitory effect on the microorganisms may, however, be produced by inhalation, respiration, digestion or imbibition of the active agent by the microorganisms.

Also within the scope of this invention is any article having a surface coated with a coating containing (i) menthol and/or isopulegol, (ii) at least one compound listed under ii) a) to f), above, and (iii) a film forming agent. The coated articles of the invention can comprise any material to which biofouling organisms are prone to attach, such as metal, wood, concrete, plastic, composite and stone. Representative examples of articles which may benefit from a coating which inhibits attachment and growth of such organisms include boats and ships, and particularly their hulls, fishing nets, berthing facilities, such as piers and pilings, buoys, offshore rigging equipment, intake screens for water distribution systems and decorative or functional cement or stone formations.

Further aspects of the present invention are the following:

- The use of a compound selected from the group consisting of any of the compounds listed under ii) a) to f) above, and mixtures thereof, as antifouling agent.
- The use of (a) a compound selected from the group consisting of any of the compounds listed under ii) a) to f) above, and mixtures thereof, or (b) a paint or coating composition of the present invention or (c) a paint according to the present invention for protecting a surface exposed to an aqueous environment from fouling organisms present in said aqueous environment.
- The use of a compound selected from the group consisting of any of the compounds listed under ii) a) to f) above, and mixtures thereof, for producing a marine paint composition for protecting a surface exposed to an aqueous environment from fouling organisms present in said aqueous environment.
- In the uses stated before the compound is preferably selected from the group consisting of menthol glycol carbonate (IIa), menthol propyleneglycol carbonate (IIb), menthol glycerin carbonate (IIc), l-menthyllactate, menthone glycerin acetal, N-ethyl-p-menthane-3-carboxamide, 2-isopropyl-N-2,3-trimethylbutanamide, menthyl methoxyacetate, menthyl 3,6-dioxaheptanoate, and mixtures thereof.

- A marine paint composition comprising

a) one or more compounds selected from the group consisting of the compounds listed under ii) a) to f) (in particular compounds from group ii) c)) above,

5 a film forming agent,

optionally, one or more typical additives, and

optionally, menthol and / or isopulegol,

wherein the total amount of components a) and, if present, d) is effective for inhibiting or preventing fouling organisms, when the marine paint is applied to a substrate and the substrate is thereafter exposed to sea water.

10

Further aspects of the invention are stated in the attached claims.

The use of a mixture of (a) one or more compounds selected from the group consisting of the compounds listed under ii) a) to f) above and (b) menthol and / or isopulegol is preferred as such mixture shows a synergistically enhanced activity (see Example 2 below).

15

The following examples are provided to describe the invention in further detail.

20

These examples are intended merely to illustrate specific embodiments of the compositions, methods and coated articles of the invention, and should in no way be construed as limiting the invention. These examples provide the results of tests conducted to determine the efficacy of certain compounds of the invention in inhibiting settlement of biofouling organisms.

25

EXAMPLE 1

Antifouling Test Methods

a.. Collection and Culture of Barnacles

Adults of the barnacle, *Balanus amphitrite* Darwin, were collected from the Sacred Heart Marine Research Center at St. Mary's College in Tuticorin, India.

30

The barnacles were crushed and the nauplius stage larvae were collected for culture to the cyprid stage following the method of Rittschof et al., J.Exp. Mar. Biol. Ecol., 82:131-146 (1984). The cyprid is the stage at which the barnacle

larva is competent to attach to surfaces. Upon attachment to a surface, the larva then undergoes metamorphosis into a barnacle.

b. Settlement Assay

Barnacle settlement assays were undertaken using the method described previously by Rittschof et al., J.Chem. Ecol., 11: 551-563 (1985). Briefly, Falcon 50x9 mm plastic petri dishes were filled with 5 ml of filtered seawater at salinity of 33-35 parts per thousand (ppt) and into which 3-day old cyprid stage larvae were added. Menthol and/or isopulegol and/or compounds listed under ii) a) to f), above, were introduced at various concentrations into the dishes containing seawater. Controls were represented by those dishes in which no test compound were added. After incubation at 28°C for 9 hours, the dishes were examined under a dissecting microscope to determine if there was any mortality. The larvae were then killed with 10% formalin and the number of attached and unattached larvae were counted. Settlement data were expressed as the percentage of the larvae attached to the bottom of the dish.

The settlement assay was used to determine the effective concentration of a number of different compounds listed under ii) a) to f), above. The effective concentration (EC_{50}) is that concentration which inhibited the settlement of fifty percent (50%) of the cyprid stage of the barnacle larvae present in a test sample. The results are shown in Table II and Table III.

The racemic (\pm) compounds are denoted with the prefix rac-.

TABLE I

COMPOUND		EC ₅₀ (mg/ml)
5	1R,2S,5R-(-)-menthol (= l-menthol)	$4 * 10^{-3}$ (see WO 01/95718)
	1S,2R,5S-(+)-menthol	0.1 (see WO 01/95718)
	rac-menthol	0.1 (see WO 01/95718)
	(-)-menthone	0.001 (see WO 01/95718)
	(-)-isopulegol	$8.8 * 10^{-5}$ (see WO 01/95718)
10	rac-isopulegol	$2.9 * 10^{-5}$
	menthylmethylether	$1.1 * 10^{-4}$
	l-menthyl propyleneglycol carbonate	$2.2 * 10^{-6}$
	l-menthyl lactate	$2.0 * 10^{-6}$
	rac-menthone glycerin acetal	$4.9 * 10^{-5}$
15	menthone glycerin acetal	$5.2 * 10^{-7}$
	d-limonene	$2.9 * 10^{-5}$

TABLE II

5	COMPOUNDS	ratio by weight	EC ₅₀ (mg/ml)
	l-menthol / l-menthone	60 : 40	1.5 * 10 ⁻⁶
	l-menthol / l-menthone / d-isomenthone	60 : 30 : 10	2.1 * 10 ⁻⁷
	l-menthol / rac-menthone	60 : 40	3.2 * 10 ⁻⁷
10	l-menthol / rac-isopulegol	50 : 50	1.8 * 10 ⁻⁵

EXAMPLE 2

Inhibition of Fouling Organisms Using a Marine Paint Composition
15 **Containing**

(-)-menthol, rac-isopulegol and l-menthol propyleneglycol carbonate
Separately and in Combination

A floating platform was constructed using layers of bamboo and styrofoam floats.
The platform was designed with holders to accommodate test panels measuring
20 4 inches x 12 inches x 0.25 inches (1 inch = 2.54 cm).

A first experimental paint was prepared, containing a biocidally effective amount of cuprous oxide and no other biocide which was used as the control. This composition consisted of 40 parts by weight of cuprous oxide, 10 parts by weight of iron oxide red, 5 parts by weight of xylene, 10 parts by weight of butyl alcohol, 5 parts by weight polyamide resin, 6 parts by weight of plasticizer. To this composition was added a combination of 0.5% by weight of rac-isopulegol, 0.25% by weight of (-)-menthol and 0.25% by weight of l-menthol propyleneglycol carbonate (Composition A). A second paint composition was prepared from the same marine paint vehicle containing cuprous oxide, to which was added 2% by weight of (-)-menthol (Composition B). A third formulation was made from the same cuprous oxide-containing marine paint vehicle, to which was added 2% by weight of rac-isopulegol (Composition C). A fourth formulation was made from the same cuprous oxide-containing marine paint vehicle, to which was added 2% by weight of l-menthol propyleneglycol carbonate (Composition D).

Solid iron panels having the above-mentioned dimensions were painted with the paint formulations thus prepared, placed in the holders in the floating platform and submerged continuously near the center of Bitac Cove in San Dionisio Bay (Philippines) for a period of 78 weeks. The panels were examined for a few minutes every three months and immediately resubmerged after photography.

After 78 weeks, the panels were removed and inspected. The numbers of barnacles attached to the panels were counted. The major fouling organisms included the barnacle, *Balanus amphitrite* communis, and the rock oyster, *Crossostrea cuculata*.

The data obtained are set forth in Table III below. These data show that rac-isopulegol, (-)-menthol and l-menthol propyleneglycol carbonate each are effective antifouling agents with settlement rates of 16.1%, 12.2% and 23.4%, respectively. When the three compounds were used in combination at the lower concentrations of 0.5% and 0.25% respectively the protective effect was more evident, with a settlement rate of 2.0%.


TABLE III

<u>Concentration (% by weight)</u>				
5	PAINT			
	COMPOSITION	racemic isopulegol	(-)-menthol propyleneglycol carbonate	% Settlement
	CONTROL	0	0	100
	COMPOSITION A	0.5	0.25	2.0
10	COMPOSITION B	—	2.0	16.1
	COMPOSITION C	2.0	—	12.2
	COMPOSITION D	—	2.0	23.4

- 15 The foregoing example clearly demonstrates that the compositions of the present invention containing menthol and/or isopulegol and compounds listed under ii) a) to f), above, are effective in preventing the attachment of fouling marine algae and planktonic organisms on the surfaces of underwater structures to which the composition is applied as a coating. These data further show the long lasting
- 20 activity of the compositions of the invention and the synergistic effect of the components on each other.

Claims:

1. A paint or coating composition comprising
 - (i) menthol and / or isopulegol,
 - (ii) a compound of formula (II)



(II)

wherein

R^a denotes $\text{C}_4\text{-C}_{20}$ -alkyl, $\text{C}_5\text{-C}_{20}$ -cycloalkyl or -heterocycloalkyl or $\text{C}_5\text{-C}_{20}$ -alkoxy, $\text{C}_6\text{-C}_{12}$ -aryl, $\text{C}_5\text{-C}_{10}$ -heteroaryl or $\text{C}_7\text{-C}_{11}$ -aralkyl;

R^b denotes an $m + w + n$ -valent aliphatic $\text{C}_1\text{-C}_8$ radical, a cycloaliphatic or heterocycloaliphatic $\text{C}_3\text{-C}_{15}$ radical, an araliphatic $\text{C}_7\text{-C}_{20}$ radical, an alkoxy- or acyloxy-containing aliphatic $\text{C}_3\text{-C}_{15}$ radical;

A and B independently of one another denote -O-, -S- or -NH-;

Y denotes hydroxy, $\text{C}_1\text{-C}_{10}$ -alkoxy, $\text{C}_2\text{-C}_6$ -acyloxy, amino, mercapto or -O-Z-O-;

Z denotes $\text{C}_1\text{-C}_6$ -alkylene;

w denotes the valency of the radical Y and

m and n independently of one another denote integers from 1 to 8, with the proviso that the sum of $m + n$ is not more than 12, and

(iii) a film forming agent.

2. A composition according to claim 1, wherein said compound of formula (II) is present in an amount from about 0.01 to about 50 percent by weight of said composition.

3. A composition according to claim 1 or 2, wherein the compound of formula (II) are menthol glycol carbonate (IIa), menthol propyleneglycol carbonate (IIb)

and menthol glycerin carbonate (IIC).

4. A composition according to any preceding claim, comprising menthol, isopulegol and menthol propyleneglycol carbonate.

5

5. A paint comprising a composition according to any preceding claim.

6. A paint according to claim 5, which is formulated as a marine paint.

10 7. Use of a composition according to any of claims 1-4 or a paint according to claim 5 or 6 for protecting a surface exposed to an aqueous environment from fouling organisms present in said aqueous environment.

8. A method for protecting a surface exposed to an aqueous environment
15 from fouling organisms present in said aqueous environment, which comprises applying to said surface a coating including menthol and/or isopulegol and at least one compound of formula (II) as defined in claim 1.

9. A method according to claim 8, wherein said coating composition is applied
20 to said surface by brushing, spraying or dipping.

10. An article having an underwater surface, at least a portion of said surface being coated with a composition according to any of claims 1-4 or a paint according to claim 5 or 6.

25

11. An article according to claim 10 in the form of a ship hull or fishing net.

12. Use of a compound of formula (II) as defined in claim 1 as antifouling agent.

30

13. Use of a compound of formula (II) as defined in claim 1 for protecting a surface exposed to an aqueous environment from fouling organisms present in said aqueous environment.

14. Use of a compound of formula (II) as defined in claim 1 for producing a marine paint composition for protecting a surface exposed to an aqueous environment from fouling organisms present in said aqueous environment.

5 15. Use of a compound of formula (II) as defined in claim 1 for synergistically enhancing the antifouling effect of (a) menthol, (b) isopulegol or (c) a mixture of menthol and isopulegol.

10 16. Use according to any of claims 12-15, wherein the compound of formula (II) as defined in claim 1 is selected from the group consisting of menthol glycol carbonate (IIa), menthol propyleneglycol carbonate (IIb), menthol glycerin carbonate (IIc), and mixtures thereof.

17. Marine paint composition comprising
15 a) one or more compounds of formula (II) as defined in claim 1,
b) a film forming agent,
c) optionally, one or more typical additives, and
d) optionally, menthol and / or isopulegol,

20 wherein the total amount of components a) and, if present, d) is effective for inhibiting or preventing fouling organisms, when the marine paint is applied to a substrate and the substrate is thereafter exposed to sea water.

18. A paint or coating composition comprising

25 (i) menthol and / or isopulegol


and

(ii) a compound selected from the group consisting of

30

a) menthyl esters of a natural occurring hydroxycarboxylic acid having 2 to 6 carbon atoms, which are in turn optionally esterified by C₁-C₄ carboxylic acids on the hydroxy group;

b) compounds of formula (I):



5

(1).

wherein


R¹ represents a C₂-C₆-alkylene radical having at least 1, but not more than 3, hydroxy group(s) and

10 either R² and R³ independently of one another represent C₁-C₁₀-alkyl which is optionally substituted by 1 to 3 radicals from the group comprising hydroxy, amino and halogen, or C₅-C₇-cycloalkyl, or C₆-C₁₂-aryl, with the proviso that the total amount of the carbon atoms of R² and R³ is not less than 3.

or

15 R² and R³ together represent an alkylene radical which, together with the carbon atom which carries the radicals R² and R³, forms a 5-7-membered ring, it being possible for this alkylene radical, for its part, to be substituted by C₁-C₆-alkyl groups;

20 d) compounds of formula (III):




(111)

wherein

25 R = H and k is a whole number from 1 to 4, or R = CH₃ and k is a whole number from 0 to 4;

e) compounds of formula (IV):




(IV)

5 wherein

R' is H or an alkyl, cycloalkyl, alkenyl, cycloalkenyl, hydroxyalkyl, alkynyl, acyloxyalkyl, alkoxyalkyl, aminoalkyl, acylaminoalkyl, carboxyalkyl radical or an alkylcarboxyalkyl radical of the formula $-C_pH_{2p}COOR''$, wherein $-C_pH_{2p}$ is a straight or branched chain alkylene group in which p is an integer from 1 to 6 and
 10 R'' is C₁-C₈-alkyl, each of said radicals containing up to 25 carbon atoms, and

R'' is hydroxy or an alkyl, cycloalkyl, alkenyl, cycloalkenyl, hydroxyalkyl, alkynyl, acyloxyalkyl, alkoxyalkyl, aminoalkyl, acylaminoalkyl, carboxyalkyl radical or an alkylcarboxyalkyl radical of the formula $-C_pH_{2p}COOR'''$, wherein $-C_pH_{2p}$ is a straight or branched chain alkylene group in which p is an integer from 1 to 6 and
 15 R''' is C₁-C₈-alkyl, each of said radicals containing up to 25 carbon atoms; with the proviso that when R' is hydrogen R'' may also be an aryl radical of up to 10 carbon atoms selected from benzyl and substituted phenyl wherein the substituents are selected from C₁-C₄ alkyl, hydroxy and C₁-C₄-alkoxy, nitro and halogen;

20 f) compounds of formula (V):



(V)

wherein

$\text{R}^{\#}$ is C_1 - C_5 -alkyl, C_1 - C_8 -hydroxyalkyl or alkylcarboxyalkyl with up to 6 carbon atoms,

R^{X} is hydrogen or C_1 - C_5 -alkyl; and

R^{Y} and R^{Z} independently are C_1 - C_5 -alkyl,

with the provisos that

R^{X} , R^{Y} and R^{Z} together provide a total of at least 5 carbon atoms, preferably 5-10 carbon atoms, and

when R^{X} is hydrogen, R^{Y} is C_2 - C_5 -alkyl and R^{Z} is C_3 - C_5 -alkyl and at least one of R^{Y} and R^{Z} is branched, preferably in alpha or beta position relative to the carbon atom marked (*) in the formula (V);

and

(iii) a film forming agent.

19. A composition according to claim 18, wherein said compounds are present in an amount from about 0.01 to about 50 percent by weight of said composition.

20. A composition according to claim 18, wherein the compound selected from (ii) a), above, is l-menthyl lactate.

21. A composition according to claim 18, wherein the compound selected from (ii) b), above, is menthone glycerin acetal.

22. A composition according to claim 18, wherein the compound selected from (ii) e), above, is N-ethyl-p-menthane-3-carboxamide.
23. A composition according to claim 18, wherein the compound selected from
5 (ii) f), above, is 2-isopropyl-N-2,3-trimethylbutanamide.
24. A paint comprising the composition of any of claims 18-23.
25. A paint according to claim 24, which is formulated as a marine paint.
10
26. Use of a composition according to any of claims 18-23 or a paint according to claim 24 or 25 for protecting a surface exposed to an aqueous environment from fouling organisms present in said aqueous environment.
- 15 27. A method for protecting a surface exposed to an aqueous environment from fouling organisms present in said aqueous environment, which comprises applying to said surface a coating including menthol and/or isopulegol and at least one compound listed under ii) a) to f) in claim 18.
- 20 28. A method according to claim 27, wherein said coating composition is applied to said surface by brushing, spraying or dipping.
29. An article having an underwater surface, at least a portion of said surface being coated with a composition according to any of claims 18-23.
25
30. An article according to claim 29 in the form of a ship hull or fishing net.
31. Use of a compound selected from the group consisting of any of the compounds listed under ii) a) to f) in claim 18, and mixtures thereof, as
30 antifouling agent.
32. Use of a compound selected from the group consisting of any of the compounds listed under ii) a) to f) in claim 18, and mixtures thereof, for protecting

a surface exposed to an aqueous environment from fouling organisms present in said aqueous environment.

33. Use of a compound selected from the group consisting of any of the compounds listed under ii) a) to f) in claim 18, and mixtures thereof, for producing a marine paint composition for protecting a surface exposed to an aqueous environment from fouling organisms present in said aqueous environment.

34. Use of a compound selected from the group consisting of any of the compounds listed under ii) a) to f) in claim 18, and mixtures thereof, for synergistically enhancing the antifouling effect of (a) menthol, (b) isopulegol or (c) a mixture of menthol and isopulegol.

35. Use according to any of claims 31-34, wherein the compound is selected from the group consisting of l-menthyllactate, menthone glycerin acetal, N-ethyl-p-menthane-3-carboxamide, 2-isopropyl-N-2,3-trimethylbutanamide, menthyl methoxyacetate, menthyl 3,6-dioxaheptanoate, and mixtures thereof.

36. Marine paint composition comprising

- (a) one or more compounds selected from the group consisting of the compounds listed under ii) a) to f) in claim 18,
- (b) a film forming agent,
- (c) optionally, one or more typical additives, and
- (d) optionally, menthol and / or isopulegol,

wherein the total amount of components a) and, if present, d) is effective for inhibiting or preventing fouling organisms, when the marine paint is applied to a substrate and the substrate is thereafter exposed to sea water.

INTERNATIONAL SEARCH REPORT

International Application No

PC P2004/003710

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D5/16 A01N37/18 A01N37/20 A01N37/36 A01N43/24
A01N47/06 A01N47/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D A01N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
	- / - -	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

20 August 2004

Date of mailing of the international search report

25.08.2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,

Authorized officer

Miao K

INTERNATIONAL SEARCH REPORT

International Application No

PC P2004/003710

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
2	X WO 99/13734 A (WITKEWITZ DAVID L ; WOLF FRED R (US); HOOK JEFFREY S (US); MCGREW GORD) 25 March 1999 (1999-03-25) page 7, line 13 - page 8, line 3 page 12, line 26 page 17, line 25 - line 30 page 28, line 5 - line 11 page 35; examples A-C examples 28-33; table 9 examples 44-47,49; table 13 examples 52-57; table 15 examples 60-65; table 17 examples 68,70-73; table 19 examples 76,78-81; table 21 examples 84-89; table 23 examples 92,94-97; table 25 examples 100-105; table 27 examples 108-113; table 29 examples 116-121; table 31 examples 124-127,129; table 33	18-23,36
1	X PATENT ABSTRACTS OF JAPAN vol. 2000, no. 13, 5 February 2001 (2001-02-05) & JP 2000 290151 A (SUNSTAR INC), 17 October 2000 (2000-10-17) abstract	18-22,36
3	P,X US 6 627 233 B1 (WITKEWITZ DAVID L ET AL) 30 September 2003 (2003-09-30) claims 1,2	18-22,36
2	X WO 94/07477 A (WARNER LAMBERT CO) 14 April 1994 (1994-04-14) examples 1,2; table I	18-20,36
1	X PATENT ABSTRACTS OF JAPAN vol. 1999, no. 11, 30 September 1999 (1999-09-30) & JP 11 152217 A (KAO CORP), 8 June 1999 (1999-06-08) abstract	18-20,36
2	X WO 00/63737 A (THOMSON CSF SEXTANT ; POTIN LAURENT (FR)) 26 October 2000 (2000-10-26) examples B-D,J; table II	18-20,36
2	X US 6 391 886 B1 (LEE KUO-CHUNG MARK) 21 May 2002 (2002-05-21) claims 1-9; examples V-VII	18,19, 21,22,36
3	X US 6 267 974 B1 (FELICIANO DONALD CARL ET AL) 31 July 2001 (2001-07-31) claims 1,7,16-22	18-20, 23,36
10		

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC P2004/003710

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9913734	A	25-03-1999	WO 9913734 A1	25-03-1999
			AU 4428197 A	05-04-1999
			AU 5726998 A	05-04-1999
			BR 9715028 A	16-10-2001
			CA 2303828 A1	25-03-1999
			EP 1014805 A1	05-07-2000
			EP 1011643 A1	28-06-2000
			RU 2214721 C2	27-10-2003
			RU 2217131 C2	27-11-2003
			WO 9913870 A1	25-03-1999
			US 2003082271 A1	01-05-2003
			US 6627233 B1	30-09-2003
JP 2000290151	A	17-10-2000	NONE	
US 6627233	B1	30-09-2003	WO 9913734 A1	25-03-1999
			AU 4428197 A	05-04-1999
			AU 5726998 A	05-04-1999
			BR 9715028 A	16-10-2001
			CA 2303828 A1	25-03-1999
			EP 1014805 A1	05-07-2000
			EP 1011643 A1	28-06-2000
			RU 2214721 C2	27-10-2003
			RU 2217131 C2	27-11-2003
			WO 9913870 A1	25-03-1999
			US 2003082271 A1	01-05-2003
WO 9407477	A	14-04-1994	AU 5298493 A	26-04-1994
			WO 9407477 A1	14-04-1994
			ZA 9307353 A	29-04-1994
JP 11152217	A	08-06-1999	NONE	
WO 0063737	A	26-10-2000	FR 2792174 A1	20-10-2000
			EP 1181613 A1	27-02-2002
			WO 0063737 A1	26-10-2000
			JP 2002542409 T	10-12-2002
			US 6715150 B1	06-04-2004
US 6391886	B1	21-05-2002	AU 3939702 A	18-06-2002
			EP 1339408 A1	03-09-2003
			JP 2004515478 T	27-05-2004
			WO 0245714 A1	13-06-2002
US 6267974	B1	31-07-2001	AT 263541 T	15-04-2004
			AU 752674 B2	26-09-2002
			AU 1863600 A	02-11-2000
			BR 9917261 A	08-01-2002
			CA 2361845 A1	26-10-2000
			CN 1348352 T	08-05-2002
			CZ 20013724 A3	13-03-2002
			DE 69916329 D1	13-05-2004
			WO 0062737 A1	26-10-2000
			EP 1169011 A1	09-01-2002
			ID 30313 A	22-11-2001
			JP 2002542176 T	10-12-2002
			PL 349282 A1	15-07-2002
			RU 2229282 C2	27-05-2004

Information on patent family members

PCT/P2004/003710

Form PCT/ISA/210 (patent family annex) (January 2004)